



ACRYL FIBRE

A fibre-reinforced liquid waterproofing acrylic that provides a seamless waterproofing system.

1. USES

- Parapet Walls.
- Ridging on tiled roofs.
- Window sills.

2. ADVANTAGES

- Excellent weathering properties.
- Tough and flexible.
- Excellent adhesion.
- Ease of application.
- Can be over coated.

3. LIMITATIONS

Do not apply **Acrylfibre** if rain is imminent.

4. COVERAGE

3 square meter per litre per coat.

5. SURFACE PREPARATION.

All surfaces should be sound, clean and free from any contaminants including rust.

6. APPLICATION

Priming

Iron and steel should be primed using a suitable corrosion resistant etch primer.

First Coat

Apply a generous coat of **Acryl Fibre** by brush (3 m² per litre).

Second Coat

Allow first coat to dry sufficiently before applying second coat.

Apply second coat in opposite direction to first coat by using a brush at a rate of (3 m² per litre).

Top Coat

The **Acryl Fibre** is UV Stable and can be left as the top coat. Alternatively a good quality decorative coating can be applied over the **Acryl Fibre**, and then applied every four to five years as a maintenance plan.



7. CLEANING

Uncured **Acryl Fibre** can be removed with water.
Cured material can only be removed mechanically.

8. DISPOSAL

Dispose in accordance with local regulations.

9. HEALTH & SAFETY

Safety data sheets –available on request

| | |
|-------------|--|
| Shelf life | 12 Month in unopened container. |
| Storage | Store under cover, and protect from frost. |
| Colour | White & Grey. |
| Surface Dry | 1 hour depending on conditions. |
| Hard Dry | 6 hours. |
| Cleaning | Uncured- water. Cured-Mechanical. |
| Coverage | 3 square meter per liter |
| Packaging | 20litre, 5litre |

SPECIFICATION

| | |
|------------------------------------|-----------|
| Mass solids % | 49-51 |
| Volume solids % | 36-38 |
| Viscosity Krebs Stormer (Ku) | 120-130 |
| Specific Gravity g/cm ³ | 1.20-1.25 |
| pH | 8.5-9.5 |
| Water Uptake (7 days in water)% | 17 |
| Elongation % | 15 |
| Tensile Strength N/mm ² | 10 |
| Surface Dry at 25 C@ 85% RH | 1 Hour |
| Hard Dry at 25 C@ 85% RH | 6 Hour |
| Shelf Life | 12 month |

The above results represent laboratory averages and are indicative
Safeguard Chemical SA reserves the right to make modifications to their products without notice.

Safeguard Chemicals SA. PO Box 1032, Sundowner 2161

Tel: +27 11 708 3603 Fax: +27 11 708 3620. E-mail: info@safeguardchem.co.za

All products should be used in accordance with the manufacturer's instructions. Whilst any information and/or specification contained herein, is to the best of our knowledge, true and accurate, no warranty is given, or implied in connection with any recommendations, or suggestions made by us, our representatives, agents or distributors as every possible variation in the method of its use or conditions under which it is applied cannot be anticipated.